

### 3.1 合成石油磺酸钠

产品 **Sodium Sulfonate NA 480 T**

特性 **NA 480 T** 是一款油溶性的合成磺酸钠，应用于防锈缓蚀剂，分散剂和乳化剂（防锈性能会随着分子量的增加而增强，而乳化性能会减弱）。通过特殊工艺制造，质量稳定。

| 技术资料                         |   | 典型<br>数值 | 规格   |      |                 |
|------------------------------|---|----------|------|------|-----------------|
|                              |   |          | 最小   | 最大   |                 |
| 密度 15°C (g/cm <sup>3</sup> ) | : | 1.02     | 0.98 | 1.03 | DIN 51 757      |
| 活性成分 (wt.%)                  | : | 61       | 60   |      | ACL-028         |
| 矿物油 (wt.%)                   | : | 34       | 32   | 36   | calculative     |
| 水分(wt.%)                     | : | 4.0      |      | 5.0  | DIN 51 777-1    |
| 无机盐 (wt.%)                   | : | 0.4      |      | 0.5  | ACL-035         |
| 平均分子量                        | : | 445      |      |      | calculative     |
| 闪点 (°C)                      | : | min. 100 |      |      | DIN EN ISO 2719 |
| 色度 (dil. 10%在白油中)            | : | 4        |      |      | ACL-014         |

应用 推荐应用于金属加工液，纺织油，清洗剂，防锈剂，涂料，乳化液，矿石浮选，印刷油墨，涂料等产品中。

存储 原装密封条件下可在室内温度下存放至少 12 个月。

The data contained herein serve as general information for our customers only and are not binding. The data contained herein have been collected to the best of our knowledge and do not constitute any advice or warranty to our customers for any specific application. It is up to our customer at their own risk to determine the suitability of each product for their individual purposes. The products are sold without any representation, warranty or guarantee either expressed or implied. Our liability is limited to the value of the supplied merchandise.